



“1+” or “3” Notification No.: 1008

Test Report No.: **28240344 001** Order No.: **93356030** Page 1 / 3

Client: **JIANGSU ZHONGTIAN TECHNOLOGY CO., LTD.**

No.1 Zhongtian Road, Hakeu Town, Budaog County, 222400, Jiangsu Province, China

Harmonised standard: EN 50575:2014 + A1:2016

Classification standard: EN 13501-6:2014

Throughout this report a comma is used as the decimal separator.

Abbreviations: ok / P = passed  
fail / F = failed

data / D = publication of data

[www.tuv.hu](http://www.tuv.hu)

## EN 60332-1-2

| Clause                               | Requirement + Test                                                    | Result - Remark | Verdict |
|--------------------------------------|-----------------------------------------------------------------------|-----------------|---------|
| <b>ZTT GJFJV-4F 7.0mm (ZTT 0774)</b> |                                                                       |                 |         |
| <b>5</b>                             | <b>Procedure</b>                                                      |                 |         |
|                                      | Sample length (600 ± 25 mm).....                                      | 615             | P       |
|                                      | Approx. outer diameter (mm).....                                      | 7,0             |         |
|                                      | Flame application time (s).....                                       | 60              | P       |
| <b>6</b>                             | <b>Evaluation of test results</b>                                     |                 |         |
|                                      | Not damaged area from lower edge of the top support (min. 50 mm)..... | 337             | P       |
|                                      | Damaged area from lower edge of the top support                       | 495             | D       |

Test Type: **Test for vertical flame propagation for a single insulated wire or cable  
1 kW pre-mixed flame**

Standard: **EN 50575:2014 + A1:2016 EN 13501-6:2014**

**EN 60332-1-2:2004 + A1:2015, EN 60332-1-1:2004 + A1:2015**

No. of samples: 1

Ambient temperature: 26,5 °C

Date of test: 2017.08.07.

Classification according to EN 13501-6: **E<sub>ca</sub>**

